

Premium Product - Technical Confirmation

Test	BS EN Standard(s)	Highest Class	Internal / External			Internal	
			Flamed Result	Sandblasted Result	Jura Result	Brushed Result	Sandblasted + Brushed Result
Slip Resistance (USRV)	BSEN1341:2001	>35	71	73	60	46	52
Water Absorption	BSEN1341:2001 BS7533-12:2006	< 2.5%	0.2%	0.2%	1.8%	0.2%	0.2%
Frost Resistance	BSEN1341:2001 BSEN12371:2001 BSEN12372:1999	> 28 Cycles	48	48	48	48	48
Flexural Strength	BSEN1341:2001 BSEN12372:1999 BS7533-12:2006	> 12 Mpa	13.6	13.6	12.3	13.6	13.6
Dimensional Accuracy	BSEN1341:2001	Class 2	2	2	2	2	2